



INDIA OFFICE
KIRPA IMPEX
Building No.11504.3rd Lane
Partap Nagar .Ludhiana
141003. India

Mobile : + 91 99153-93833
Tel : + 91 161 5018855
Fax : 161 2544501.
[E mail :info@kirpaimpex.com](mailto:info@kirpaimpex.com)

USA OFFICE
STEELPAPER
INDUSTRIES
841 South Albert Ave.
South Bend.
Indiana-46619 USA

WASTE PAPER SPECIFICATIONS- EUROPE ORIGIN

GRADE# SPECIFICATION: Group I Ordinary Grade

1.01 Mixed Paper and Board [Unsorted] but unusable materials

A mixture of various grades of paper and board without restriction On short fibre contents.

1.02 Mixed Papers and Board [Sorted]

A mixture of various qualities of paper and board, containing a Maximum of 40% of Newspapers and magazines.

1.03 Grey board

printed and Unprinted white lined and unlined grey board or mixed board , free corrugated material.

1.04 Supermarket corrugated paper and board

Used paper and board packaging ,containing a minimum of 70% Of corrugated board ,the rest being solid board and wrapping papers.

1.05 Old corrugated containers

Used boxes and sheets of corrugated board of various qualities.

1.06 Unsold magazines

Unsold magazines with or without glue.

1.08 Mixed newspaper and magazines I

A mixture of newspaper and magazines, containing a minimum of 50% of newspapers with or without glue.

1.09 Mixed newspaper and magazines II

A mixture of newspapers and magazines containing a minimum Of 60% of newspaper with or without glue.

1.10 Mixed Magazines and Newspapers

A mixture of newspapers and magazines containing a minimum Of 60% of magazines with or without glue.

Group II –Medium Grades

2.01 NewsPapers

Newspapers containing a maximum of 5% of newspapers or Advertisements colored in the mass.

2.02 Unsold newspapers.

Unsold daily newspapers free from additional inserts or illustrated Material coloured in the mass.

2.05 Sorted office paper

Sorted office paper.

2.06 Colored letters

Correspondence in mixed papers colored in the mass with Or without print of priming or writing paper free from carbon Paper and hard covers.

2.07 White wood free books

Books including misprints of books, without hard covers, mainly Of wood free white paper, black printed only. Containing a maximum Of 10% of coated paper.

2.08 Colored wood free magazine

Coated or uncoated magazines white or colored in the mass Free from non-flexible Covers, bindings ,non-dispersible inks and adhesives poster papers, labels or label trim. May include heavily printed Circulars and colored in the mass shavings. Containing a maximum of 10% mechanical pulp based papers.

2.10 Bleached woodfree PE-coated board

Bleached woodfree PE-coated board paper from board manufacturers And converters.

Group III –High Grades.

3.02 Mixed Lightly coloured woodfree printer shavings

Mixed shavings of printing and writing papers lightly coloured in the mass containing a minimum of 90% of woodfree paper.

3.03 Woodfree binders

White woodfree lightly printed shavings with glue free from paper coloured in the mass. May contain a maximum of 10% of mechanical pulp based paper.

3.04 Tear White Shaving

White woodfree lightly printed shavings without glue free from wet-strength Paper and paper colored in the mass.

3.05 White woodfree letters

Sorted white woodfree writing papers. originating from office record free from cash book, carbon paper and non-water soluble.

3.06. White business forms

White woodfree printed business forms.

3.08. Printed bleached sulphate board

Heavily printed sheets of bleached sulphate board ,without glue , polycoated Or waxed materials

3.09. Lightly printed bleached sulphate board

Lightly printed sheets of bleached sulphate board without glue , polycoated or waxed Materials.

3.10. Multiprinting

Woodfree , coated ,lightly printed ,free from wetstrength paper or paper coloured in the Materials.

3.16 White woodfree coated paper,without glue

Shaving and sheets of white unprinted unprinted woodfree coated paper, without glue.

3.17 White Shaving

Shavings and sheets of white unprinted paper, free from newsprint and magazine paper
Containing a of 60% of woodfree paper, may contain a maximum of 10% of coated paper
Without glue.

3.18 White woodfree shavings

Shaving and sheets of white unprinted woodfree paper ,may contain a maximum of 5%
Of coated paper without glue.

3.18.1 White woodfree uncoated shavings

Shavings and sheets of white unprinted woodfree paper , free from coated Paper without glue

3.19 Unprinted bleached sulphate board

Unprinted sheets of bleached sulphate board , without glue,polycoated or waxed Materials.

Group IV-Kraft Grades

4.03 Used corrugated Kraft I

Used boxes of corrugated board with kraft liners only,the fluting made from chemical or
Thermo-chemical pulp.

4.02. Used corrugated Kraft II

Used boxes of corrugated board with liners of kraft or testliners but having at least one liner
Made of kraft.

